

# 8332B

## 1/32" BLACK POLYETHYLENE DIFFERENTIAL DOUBLE COATED FOAM TAPE

### PRODUCT DESCRIPTION


#### Double Coated Tape

8332B is a 1/32" thick black closed cell, crosslinked polyethylene foam coated with rubber based adhesive on one side and acrylic based adhesive on the other with a 4 mil blue poly liner.

### FEATURES & BENEFITS

- Easily die cut
- Low application temperature
- High immediate bond
- Great chemical resistance
- Good conformability, cushioning, & vibration damping
- Low compression set

### PRODUCT CONSTRUCTION



### PRODUCT SPECIFICATIONS

| Test                              | Typical Value |               | Typical Value (Metric) |               | Test Method |
|-----------------------------------|---------------|---------------|------------------------|---------------|-------------|
| Product Thickness (Total)         | 35.25         | mils          | 0.895                  | mm            | PSTC-133    |
| Adhesive Thickness (Liner Side)   | 2.00          | mils          | 0.051                  | mm            | PSTC-133    |
| Carrier Thickness                 | 31.25         | mils          | 0.794                  | mm            | PSTC-133    |
| Adhesive Thickness (Exposed Side) | 2.00          | mils          | 0.051                  | mm            | PSTC-133    |
| Peel Adhesion                     | 70            | oz/in         | 19.45                  | N/25mm        | PSTC-101    |
| Tack                              | 25            | oz            | 709                    | g             | ASTM D 2979 |
| Shear Adhesion                    | >24           | hrs @ 2.2 psi | >24                    | hrs @15.2 kPa | PSTC-107    |
| Tensile Strength                  | 100           | lb/in         | 438                    | N/25mm        | PSTC-131    |
| Elongation                        | 230           | %             | 230                    | %             |             |
| Minimum Service Temperature       | 50            | °F            | 10                     | °C            |             |
| Maximum Service Temperature       | 155           | °F            | 68                     | °C            |             |

Tested values are typical under standard conditions and are not intended to be used for specification development. Technical data is believed to be true and accurate; Adhesive Applications recommends that the purchaser test for performance and fitness of use in all applications.

### Adhesive Applications - The Adhesive Solutions Company

41 O'Neill Street  
Easthampton, MA 01027

413-527-7120 Main  
800-356-3572 Toll Free U.S.

[www.adhesiveapps.com](http://www.adhesiveapps.com)

**Adhesive**  
Applications™

Rev A

7/24/2018

